

Test Name	Test Method	Result*	Requirement
Density (lb/cu.ft)	ASTM C-97	189.90	160.00
Water Absorption (%)	ASTM C-97	0.16%	0.40%
Modulus of Rupture (psi) **	ASTM C-99	5,500	1,500
Compressive Strength (psi) **	ASTM C-170	30,100	19,000
Flexural Strength (psi) **	ASTM C-880	5,400	1,200
Dynamic Coefficient of Friction (DCOF), Wet			
• Waterjet Finish	ANSI/NFSI B101.3-2012	0.79	
• Thermal Finish	ANSI A137.1/A326.3	0.80	
• Honed Finish	ANSI A137.1/A326.3	0.49	

*Average values. ** Dry/Perpendicular

The product testing data above is presented as provided to Blackhill Granites, LLC by the quarrier or supplier of the stone.

Design with inspiration. **Build with confidence.**

101 E. Culpeper Street, Suite 101 Culpeper, VA 22701
 Sales & Service: (540) 825-9044 | sales@blackhillgranites.com

Doc.2023.02.01 Rev.02
BlackhillGranites.com